

A1  
cont

in regard to mixture A, constituents A1 + A3 where constituent A1 is platinum in the form of a platinum complex or compound and constituent A3 [consists of] comprises a combination of FeO and Fe<sub>2</sub>O<sub>3</sub>;

in regard to mixture B, constituents B1 + B2 where constituent B1 has the meaning of constituent A1 of 1 and constituent B2 [consists of] comprises cerium (IV) oxide and/or hydroxide;

in regard to mixture B, constituents B1 + B3 where constituent B1 has the meaning of constituent A1 of 1 and constituent B3 [consists of] comprises a combination of cerium (IV) oxide and/or hydroxide and titanium oxide TiO<sub>2</sub>; or

SUB  
B1

in regard to mixture C, constituents C1 + C2 where constituent C1 has the meaning of constituent A1 of 1 and constituent C2 consists of a combination of constituent B3 mentioned in 3 and constituent A3 mentioned in 1;

the amounts of the various constituents A1, A3, B1, B2, B3, C1 and C2, and the ratios that may exist between the amounts of some of them in the case of combinations, lie within the ranges mentioned below;

the amount of platinum, expressed in parts by weight of elemental platinum, lies within the range going from 1 to 250 ppm with respect to the total weight of the polyorganosiloxane constituent(s) of the curable compositions D; and

the amounts of constituents A3, B2, B3 and C2 of mixtures A, B and C, expressed in parts by weight of the constituent, lie within the range going from 0.5 to 30 parts by weight per 100 parts of the polyorganosiloxane constituent(s) of the curable compositions D;

in constituent A3 (a combination), the ratio of the amount by weight of FeO to that of Fe<sub>2</sub>O<sub>3</sub> lies within the range going from 0/1:1 to 9:1;

in constituent B3 (a combination), the ratio of the amount by weight of cerium (IV) oxide and/or hydroxide to that of TiO<sub>2</sub> lies within the range going from 0.6:1 to 6:1;

in constituent C2 (a combination), the ratio of the amount by weight of constituent A3 to that of constituent B3 lies within the range going from 0.02:1 to 1:1;

in a polyorganosiloxane composition D for obtaining a silicone elastomer, either crosslinking at room temperature or with the heat from polyaddition reactions in the presence of a platinum catalyst, or crosslinking at high temperature by the action of an organic peroxide or peroxides;

it being possible for constituent A1, B1 or C1 of the additive to be present in the form of the catalytic platinum which is contained in a polyorganosiloxane composition D crosslinking at room temperature or with the heat from polyaddition reactions.

Claim 2, line 1, delete "Use" and insert --The method--;

Claim 2, lines 1-2, delete "1, characterized in that" and insert --11, wherein--;

Claim 2, lines 7-8, delete "in particular";

Claim 3, line 1, delete "Use" and insert --The method--;

Claim 3, lines 1-2, delete "characterized in that" and insert --wherein--;

Claim 4, line 1, delete "Use" and insert --The method--;

Claim 4, line 1, delete "or 3";

Claim 4, line 3, delete "characterized in that" and insert --wherein--;

Claim 5, line 1, delete "Use" and insert --The method--;

Claim 5, lines 1-2, delete "characterized in that" and insert --wherein--;

Claim 5, line 5, delete "the";

Claim 6, line 1, delete "Use" and insert --The method--;

Claim 6, lines 1-2, delete "claims 2 to 5, characterized in that" and insert --claim 2,  
wherein--;

Claim 6, lines 6-7, delete "given above in claim 4 or 5";

Claim 7, line 1, delete "Use" and insert --The method--;

Claim 7, lines 1-2, delete "or 3, characterized in that" and insert --wherein--;

Claim 7, line 15, delete "the";

Claim 8, line 1, delete "Use" and insert --The method--;

Claim 8, lines 1-2, delete "or 3, characterized in that" and insert --wherein--;

Claim 9, line 3, delete "as well as" and insert --and--;

Claim 9, lines 4-5, delete "characterized in that they" and insert --which--;

Claim 9, delete lines 7-9;

Claim 9, line 10, delete "use, in claim 1";

Claim 10, line 2, delete "characterized in that they consist of" and insert --which  
comprise--.